

PATTY MADDEN

S O F T W A R E

PATTERN SPECIFICATIONS:

CAPRENI

PQ:SIS 4.11.07

GENERAL	
TOTAL WEIGHT - OZ. LIN/YD	32.00
WIDTH - IN. (MIN)	54.00
GAUGE (MILS)	50.00
TOPSKIN THICKNESS (MILS)	10.00
EMBOSSING	CAPRENI
PRINT(S)	CUSTOM-TIP
LUSTRE	SPECIAL
HAND	SPECIAL

SUBSTRATE	100% POLYESTER
TYPE	HI-LOFT ² ™
WEIGHT - OZ. LIN/YD	5.75

MISCELLANEOUS	
ANTISTATIC (ASTM D-257)	PASS
SULFIDE STAINING	PASS

CROCKING CFFA-7A	
DRY	PASS
WET	PASS

FLAME RETARDANCY	
FMVSS 302	PASS
BOSTON FIRE CODE	PASS
NY/NJ PORT OF AUTHORITY	PASS
CALIF. TECH. BULLETIN	PASS
FAR 25.853 B	PASS
BIFMA	PASS
BFD IX-1	PASS
MASS. 527 CMR 21.00	PASS
UFAC FABRIC, CLASS 1	PASS
NFPA 260-CLASS 1	PASS
IMO STANDARD A.652(16)8.2 & 8.3	PASS
BRITISH STANDARD BS EN 1021-1 & 1021-2	PASS

ADHESION - ASTM D-751-89		
POUNDS/INCHES (MIN)	WARP	7.00
	FILL	6.00
TENSILE STRENGTH - ASTM D-751-89		
POUNDS (min)	WARP	140.00
	FILL	115.00
ELONGATION - ASTM D-751-89		
% (min).	WARP	65.00
	FILL	157.00
TEAR STRENGTH - FED STND 191 M5134		
POUNDS	WARP	65.00
	FILL	54.00
STITCHING STRENGTH DIN 54301		
POUNDS (MIN)	WARP	16.20
	FILL	12.00
PERMABLOK® ADVANCED VINYL PROTECTION		
ABRASION - FED STND 191 M5304		
WYZENBEEK - WIRE SCREEN		NO CHANGE
		@100,000 CYL
ANTIBACTERIAL ACTIVITY ASSESSMENT		
(TEST METHOD AATCC 147-1988)		PASS
ANTIFUNGAL ACTIVITY ASSESSMENT		
(TEST METHOD ASTM G-21-90)		PASS
ULTRAVIOLET AATCC 16 XENO TEST 150		
(300 HOURS)		PASS
MILDEW - VENTRON B-20 ASTM G-21		
		PASS
COLD CRACK - FED STND 191 M5874 -10F		
ROLLER		PASS
MANDREL		N/A