



writeMAGNETIC48 (dry erase wallcovering)

technical data sheet

Total Weight: 48 oz / sq yd

Top Film Weight: .95 oz / sq yd

Backing: 100% Polyester

Laminate Thickness: 1 mil

Total Thickness: 30 mils

Widths: 47"/48"

Flame Resistance: Class A (ASTM E-84)

Tensile Strength: 275 x 208 lbs (ASTM D 5034)

Tear Strength: 11.8 x 7.2 lbs (ASTM D 2261)

Solvent Resistance: 1,000 Double rubs w/ MEK (ASTM D 4752)

Colorfastness: Class 4.5 - 5 at 200 AFU (AATCC 16E)

Abrasion Resistance: 20,000 Double Rubs - Wyzenbeek (ASTM D 3597)

Note: For best results, rare earth or Neodymium magnets are recommended for WriteMagnetic48.