

everMagnetic60

technical data sheet

Total Weight:	54 oz / sq yd
Film Weight:	.95 oz / sq yd
Backing:	100% Polyester (Non-woven)
Laminate Thickness:	1 mil
Total Thickness:	30 mils
Width:	60"
Flame Resistance:	Class A (ASTM E-84)
Solvent Resistance:	1000 Double rubs w/ MEK (ASTM D 4752)
Colorfastness:	Class 4.5 - 5 at 200 AFU (AATCC 16E)
Abrasion Resistance:	20,000 Double Rubs / Wyzenbeek (ASTM D 3597)